



OXIDOL

ANTICORROSIVE PRIMER

GENERAL CHARACTERISTICS

Excellent anticorrosive primer, with low VOC content and lower odor during application. Gives excellent anticorrosive protection to metal surfaces even in strong corrosive conditions and very good adhesion. It doesn't contain toxic pigments. Easy to apply with very good leveling.

TECHNICAL CHARACTERISTICS

- Texture** : Satin 14-20 units in 60°.
- Specific gravity** : 1,41 – 1,44 kg/lit (white).
1,38 – 1,41 kg/lit (grey-brown).
- Covering power** : 14-16 m²/lit per layer depending on the surface.
- Dilution** : Up to 5% on volume with SMALTOLUX WHITE SPIRIT for application by brush or roller and for spray application use up to 18% on volume with No1 thinner of **VECHRO**.
- VOC class** : "One-pack performance coatings. Primer for ferrous substrates" Type SB. VOC limit =500 gr/lit. Max VOC of product ready for use= 450 gr/lit. It fulfills the requirements of E.C. legislation after 2011. VOC: organic volatile compounds with boiling point < 250°C.
- Drying** : 1-1½ hours touch free. Drying through 3-4 hours.
- Recoatibility** : Recoatable 18 hours after application or after first layer's hardening. These times prolong under cold and wet weather conditions.
- Adhesion on metallic surfaces** : Excellent adhesion (GT0 – GT1) .
- Elasticity** : Very good elasticity (Great Resistance to bending 180° on a rod diameter 3mm without cracking or flaking).
- Anticorrosive protection** : Test salt spray results- 200h on 80µm dry film - are:
α) Degree of blistering 8M/55.
β) Degree of rusting 0,031100.
- Shades** : Brown, grey, white.

PACKING: Grey & Brown: 375ml, 750ml, 2,5lt & 5lt.
White: 375ml, 750ml & 2,5lt.

APPLICATION EQUIPMENT: Brush, roller, airless spray.

SURFACE PREPARATION

Sandpaper well and clean the surface of dust, oil, cropped paints, and dampness.

APPLICATION

Stir well. Apply one or two coats **OXIDOL**. For better protection, primed surfaces should be painted with the suitable finish paint such as **GUMILAK metal**, **SMALTOLUX extra** or any enamel paint from **VECHRO**.

CLEANING EQUIPMENT

While working keep your equipment wet, either in the pot, or in the paint lauder. Strain well your tools from paint back to the pot and clean immediately with thinner and afterwards with water and soap.

APPLICATION CONDITIONS

Temperature 8-30°C and relative humidity lower than 80%. Adverse conditions will delay drying and hardness development properties.

STORAGE CONDITIONS

Close well after use. Store in a cool place. Protect from freezing and direct sun exposure.

SAFETY INSTRUCTIONS

- Keep out of the reach of children.

LABELLING

OXIDOL anticorrosive primer extra needs no hazard symbols according to EC and National legislation.

* More information in Material Safety Data Sheets (MSDS).

ERROR: syntaxerror
OFFENDING COMMAND: --nostringval--

STACK:

/Title
(
/Subject
(D:20101116124322)
/ModDate
(
/Keywords
(PDFCreator Version 0.8.0)
/Creator
(D:20101116124322)
/CreationDate
(User)
/Author
-mark-