



POOL PLUS ONE

CHLORINATED RUBBER PAINT FOR SWIMMING POOLS

GENERAL CHARACTERISTICS

POOL PLUS ONE is a high quality paint suitable for swimming pools, based on chlorinated rubber resin, which creates a tough and elastic film. It is proposed for the painting of both new or repainted swimming pools made by concrete. Has great adhesion on these surfaces. It doesn't contain lead or other toxic substances and doesn't pollute water, towards which has great and permanent resistance. It is recommended for swimming pools or surfaces with permanent touch to fresh water or seawater. It has excellent resistance to chlorine and other preservative chemicals, which used. Gives excellent decorative results without complicated application. It is easy to use and apply after the appropriate pretreatment of the substrate. Very rapid drying even in adverse weather conditions.

TECHNICAL CHARACTERISTICS

- Texture** : Satin up to 20-30 units 60°.
- Specific Gravity** : 1,10 – 1,16 kg/lit (depending on color shade)
- Covering power** : 7 - 9 m² /lit per coat, depending on surface's absorbency.
- Dilution** : 8-10% with Thinner No1 of VECHRO for application by brush or roller and 10-20% for application by spray.
- VOC class** : "Binding Primers, coatings designed to impart hydrophobic properties" Type SB. VOC limit =750 gr/lit. Max VOC of product ready for use= 745 gr/lit. VOC: organic volatile compounds with boiling point < 250°C.
- Drying** : Touch free in ½-1 hour.
- Recoatibility** : 16 hours after the application. One should check the down corners of the pool and evaluate if the coating is wet or not in that area. If yes, please wait until complete drying and evaporation of the solvents.
- Color Shades** : Light turquoise and other shades upon request.

PACKING: 4lt.

APPLICATION EQUIPMENT: Brush, roller, spray. Clean the tools with Thinner

SURFACE PREPARATION

NEW CONCRETE SURFACES: To make sure of a successful paint adhesion we recommend to prime the surface by 10% Hydrochloric acid to open by this way the pores of the substrate and enhance even more the adhesion. Rinse the walls of the pool with plenty of water and clean of cropped paints and rust. Keep at least one week before painting on very well drying surfaces.

OLD, ALREADY PAINTED SURFACES: The surface has to be cleaned of dust, oil, cropped old paints, rust etc and should be sanded. Glossy surfaces (i.e surfaces painted with two component coatings) should be sanded and cleaned very well before painting to obtain good adhesion.

Prime the new or the old well prepared surface by diluting the POOL PLUS ONE around 20% with Thinner No1 of VECHRO.

APPLICATION

Apply two coats of POOL PLUS. Avoid to built total film thickness higher than 120 µm dry.

One could use the swimming pool and fill it with water after the complete drying of the coating (around 14 days).

CLEANING EQUIPMENT

While working keep your equipment wet, either in the pot, or in the paint lauder. Strain well your tools from paint back to the pot and clean immediately with thinner No1 VECHRO and water and soap.

APPLICATION CONDITIONS

Avoid painting onto wet surfaces and under strait sunlight.

Temperature 8-30 °C and relative humidity lower than 80%. Contrary weather conditions may degrade paint's quality.

STORAGE CONDITIONS

Close well after use. Store in a cool place. Protect from sun exposure.

SAFETY INSTRUCTIONS

- Keep out of the reach of children

LABELLING

➤ **HARMFUL**

* More information in Material Safety Data Sheets (MSDS).