



RELIEF SMALTOPLAST

ACRYLIC WITH TEXTURE EFFECTS PAINT

GENERAL CHARACTERISTICS

High quality texture emulsion paint 100% acrylic. Due to this special composition gives a perfect texture decoration surface. It can be used to paint new or old painted walls. Suitable for protection and decoration of interior and exterior surfaces such as walls, plasters and concrete surfaces if they are well primed.

TECHNICAL CHARACTERISTICS

- Texture** : Flat.
- Specific gravity** : 1,65 – 1,70 kg/lt.
- Covering power** : 1,0 – 1,5 m²/kg per layer depending on the surface.
- Dilution** : Ready for use.
- VOC class** : **a.** "Exterior wall coatings of mineral substrate". Type WB. VOC limit = 40 gr/lt. **b.** "Interior matt coatings for walls and ceilings". Type WB. VOC limit = 30 gr/lt. Max VOC of product ready for use = 20 gr/lt. It fulfills the requirements of E.C. legislation after 2011. VOC: organic volatile compounds with boiling point < 250°C.
- Drying** : Dry to touch in ½ - 1 hour. The paint obtains its hardness after 3-4 weeks.
- Recoatibility** : 4 – 6 hours. These times could elongate under cold and wet weather conditions.
- Color shades** : White.

PACKING: 5 kg & 15 kg.

APPLICATION EQUIPMENT: Thick brush, spatula, spongy roller for special texture.

SURFACE PREPARATION

Clean the surface of dust, oil, cropped paints and dampness. Sandpaper well and prime surfaces painted with white lime or new concretes with Smaltoplast Universal Primer or SMALTODUR, while **very dirty surfaces** (damp, nicotine, ink, fungi, graffiti, oil spots etc) should be primed with special primer SMALTOX hydro or SMALTOX mono.

APPLICATION

Stir well before use. Apply one or two coats of RELIEF SMALTOPLAST by thick brush, spatula or roller without dilution. Before drying we pass over the laid surface with a special spongy roller in order to create the decoration.

CLEANING EQUIPMENT

While working keep your equipment wet, either in the pot or in the paint launder. Strain well your tools from paint back to the pot and clean immediately with water and soap.

APPLICATION CONDITIONS

Temperature 8-30 °C and relative humidity lower than 80%. Contrary weather conditions may degrade paint's quality. New cementinous surfaces should be dried and cured 3-4 weeks before priming.

STORAGE CONDITIONS

Close well after use. Store in a cool place. Protect from freezing and sun exposure.

SAFETY INSTRUCTIONS

- Keep out of the reach of children.

LABELLING

RELIEF SMALTOPLAST needs no danger symbols according to EC legislation.