



VELATOURA SMALTOLUX

UNDERCOAT FOR WOOD SURFACES

GENERAL CHARACTERISTICS

New generation undercoat based on special alkyd resins for interior and exterior use with low VOC content and lower odor during application. It can be used on surfaces of wood and MDF. Due to its special composition gives good fill, easy application and excellent brush ability, great covering, easy sanding and quick recoat ability.

TECHNICAL CHARACTERISTICS

- Texture** : Flat, gloss 8-10 units in 60°.
- Specific gravity** : 1,50-1,53 kg/lit.
- Covering power** : 14-18 m²/lit per layer depending on the surface.
- Dilution.** : Up to 4% on volume with SMALTOLUX WHITE SPIRIT for application by brush or roller, for airless spray application use up to 4% on volume with No 1 thinner of VECHRO.
- VOC class** : "Interior/exterior trim and cladding paints for wood and metal" Type SB. VOC limit =300 gr/lit. Max VOC of product ready for use= 290 gr/lit. The paint contains also solvents which are not considered as VOC. It fulfills the requirements of E.C. legislation after 2011. VOC: organic volatile compounds with boiling point < 250°C.
- Drying** : Touch free after 1-2 hours.
- Recoatibility** : Recoatable after 6-10 hours from application or after first layer's hardening. These times prolong under cold and wet weather conditions.
- Color Shades** : White. It could be coloured in off-white and pastel shades and **only** via **COLOR MOODS** VECHRO tinting system.

PACKING: 750ml, 2,5lt & 5lt

APPLICATION EQUIPMENT: Brush, roller, spraygun.

SURFACE PREPARATION

Clean the surface of dust, oil, cropped paints and dampness. Sandpaper well

APPLICATION

Stir well. Apply one or two coats VELATOURA SMALTOLUX extra. For better protection, primed surfaces should be painted with the suitable finish paint such as SMALTOLUX extra or any enamel paint from VECHRO.

CLEANING EQUIPMENT

While working keep your equipment wet, either in the pot, or in the paint lauder. Strain well your tools from paint back to the pot and clean immediately with thinner and water and soap.

APPLICATION CONDITIONS

Temperature 8-30 °C and relative humidity lower than 80%. Contrary weather conditions may degrade paint's quality.

STORAGE CONDITIONS

Close well after use. Store in a cool place. Protect from freezing and direct sun exposure.

SAFETY INSTRUCTIONS

- Keep out of the reach of children.

LABELLING

VELATOURA SMALTOLUX extra needs no hazard symbols according to EC and National legislation.

*** More information in Material Safety Data Sheets (MSDS).**